

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C23F 1/00, E03C 1/04</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/30733</b> <b>(43) International Publication Date:</b> 16 July 1998 (16.07.98)
<b>(21) International Application Number:</b> PCT/US98/00008 <b>(22) International Filing Date:</b> 7 January 1998 (07.01.98)  <b>(30) Priority Data:</b> 08/780,478 7 January 1997 (07.01.97) US  <b>(71) Applicant (for all designated States except US):</b> GLOBE VALVE CORPORATION [US/US]; P.O. Box 278, Delphi, IN 46923 (US).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> REGELBRUGGE, Michael, W. [US/US]; P.O. Box 162, Reynolds, IN 47980 (US). RICHEY, George, V. [US/US]; 3205 Walton Street, Lafayette, IN 47905 (US). COTE, Edward, L. [US/US]; 48751 Thornburg, Novi, MI 48374 (US). TICKANEN, Lane, D. [US/US]; 5319 Brody Drive, Madison, WI 53705 (US).  <b>(74) Agents:</b> ROCKEY, Keith, V. et al.; Rockey, Milnamow & Katz, Ltd., Two Prudential Plaza, Suite 4700, 180 North Stetson Avenue, Chicago, IL 60601 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> PROCESS FOR TREATING BRASS COMPONENTS TO REDUCE LEACHABLE LEAD  <b>(57) Abstract</b>  A process for the treatment of brass components to reduce leachable lead therefrom when the component is exposed to water in which the brass component is first treated with an aqueous caustic solution to remove some of the leachable lead therefrom. Thereafter, the brass component is leached to remove excess caustic and then contacted with a water soluble carboxylic acid to remove most of the remaining leachable lead. It has been found that the efficiency of the process can be significantly enhanced through the use of ultrasonic agitation to ensure intimate contact between the treating solutions and the brass component. In the practice of the invention, the amount of lead removed is sufficient to meet the most stringent regulatory requirements for water quality.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PROCESS FOR TREATING BRASS COMPONENTS  
TO REDUCE LEACHABLE LEAD

This invention is directed to the treatment of brass components to reduce leachable lead, particularly when the brass component is exposed to water.

Background Of the Invention

As is well known in the art, brass is an alloy composed principally of copper, lead and zinc and is widely used in a variety of applications in which it comes into contact with substances intended for human consumption. Brass has been widely used for plumbing fittings, bronze alloy and a host of other applications. Perhaps the most widespread application of brass is its use in the manufacture of faucets, valves, fittings and related products intended for use in delivering potable water within a commercial or residential structure. In that application, brass alloys are composed primarily of copper and zinc, with relatively small amounts of lead having been added to render the brass workable and machinable.

Such machinability is desirable in that it facilitates finishing of the components of faucets, valves, fittings and related products and cutting of threads and the like.

It is well known that lead atoms, because of their atomic size, are larger than copper or zinc and, as a result, lead exhibits a relatively low solubility in solid solution in brass alloys. That, in turn, promotes the tendency of lead to precipitate in lead-rich regions dispersed throughout brass

alloys. The tendency toward precipitation is particularly notable near the surface of such brass components. That leads to the advantage of improving the machinability of the brass adjacent to the surface thereof, but, at the same time, increases the tendency of lead present on the surface to leach into water.

For many years, the amount of lead leached into foods and liquids from modern lead-containing plumbing was generally regarded as low enough that it presented no substantial risk to persons ingesting foods and liquids coming in contact with such plumbing and like brass components. However, recent standards have significantly limited the amount of permissible leaching of lead and lead exposure at both the state and federal levels. One such example is the Safe Drinking Water Act, amended in 1988 to limit lead in solders and fluxes to 0.2% and to limit lead in public water supply pipes and fittings to 8%.

Similarly, efforts have been underway to limit the amount of lead found in food or water. California, for example, has promulgated regulations limiting lead exposure of an individual to less than 0.5 micrograms per day. On the Federal level, the EPA, in 1991, restructured the standard of lead in drinking water from 50 parts per billion to 15 parts per billion.

While the amount of lead that can be leached from brass plumbing components is generally low, it is nonetheless possible that the amount of lead that can be leached from such components may exceed current or planned standards. It has been proposed that standards be made even more stringent so that lead is omitted totally from the brass alloy or that the brass be treated so that minimum quantities of lead may be leached from such brass components.

It has also been proposed to control lead by chemical treatment to cause the lead to precipitate from water or to change its oxidation kinetics. To that end, it has been suggested that lead may be eliminated or minimized by controlling the pH of water containing trace amounts of lead using alkaline treating agents such as calcium oxide, calcium chloride and alkali metal hydroxides, carbonates and bicarbonates. It has also been proposed to employ alkaline phosphate salts and silicates to minimize corrosion. Either of those treatment steps, when used alone, may not be effective in water at some pH levels or such treatments, when used alone, may require high concentrations and extended periods of time to assure effectiveness.

Various other techniques have been used in the prior art to minimize the leaching of lead into drinking water. For example, it has been suggested that brass faucets, valves, fittings and related products can be treated in a copper chloride bath maintained at a low pH. Unfortunately, however, the effectiveness of that treatment is somewhat erratic, and the low pH's required can represent a health hazard to workers. Similarly, other copper treatments such as treatment with copper acetate have likewise been proposed, but those techniques are expensive and may be difficult to operate, particularly in terms of the removal of copper ions from waste waters.

It is accordingly an object of the present invention to provide a simple and inexpensive process for the treatment of brass components, such as faucets, valves, fittings and related products, to reduce leachable lead when the component is exposed to water.

It is a more specific object of the invention to provide a method for the treatment of brass components which is

equally effective in the treatment of red brass along with yellow brass.

It is yet a further object of the invention to provide a method for the treatment of brass components to reduce leachable lead therefrom which is simple and inexpensive to operate and which is effective in meeting current regulatory standards.

It is yet a further object of the invention to provide a method for the treatment of brass components which has the capability of providing dramatically reduced "Q Statistics," which are used as the current standard by which lead content of potable water is determined.

#### Summary Of The Invention

The concepts of the present invention reside in a process for the treatment of brass components to reduce leachable lead therefrom in which the brass components are chemically treated to remove substantially all of the leachable lead, including the lead from the lead-rich regions near the surface of the fittings. The process is applicable to remove leachable lead and certain other metals from brass plumbing fixtures and fittings such as faucets, shower heads, valves, pipes, pipe fittings, water meters, water pressure and flow regulators meeting the National Sanitation Foundation ("NSF") requirements for such fittings as well as the requirements of the various states to provide water containing less than 11, and preferably less than 5, parts per billion of lead. In contrast, for example, red brass components (not treated using the invention) have been known to provide water sometimes containing in excess of 400 parts per billion of lead.

In the practice of the invention, the brass component is first treated with a hot caustic wash solution to remove dirt and residues from the casting of such components and to remove most of the leachable lead from the component. After rinsing with water, the component is then dipped in a water soluble carboxylic acid, and preferably acetic acid, to remove substantially all of the remaining leachable lead of the component. It has been found that the specific combination of treatment steps insures that the leachable lead from the treated components meets the most demanding of the regulatory standards.

In accordance with one embodiment of the invention, it has been found that, in some cases, it is advantageous to employ what can be described as a chemical milling operation as a pretreatment step to remove surface metal from the interior of such plumbing fixtures. In accordance with this embodiment of the invention, it has been found that the treatment of the plumbing fixtures with a strong acid can be used to remove surface metal in those situations where the interior of such plumbing fixtures have surface roughness. That technique is particularly advantageous as a pretreatment for red brass.

In accordance with another embodiment of the invention, it is also possible, as a last treatment step after treatment with the water soluble carboxylic acid, to treat the plumbing fixtures with a phosphorous-containing acid, and preferably phosphoric acid. It has been found, depending somewhat on the characteristics of the plumbing fixtures and the brass alloys from which they are made, that the treatment step utilizing a phosphorous-containing acid, acid salt or salt derived from alkali metal served to substantially remove any remaining residual trace amounts of leachable lead, if any, from the plumbing fixtures and passivate the brass component against corrosion.

It has been found that the method is effective not only in the treatment of yellow brass but also in the treatment of red brass.

#### Detailed Description Of The Invention

In the practice of the present invention, a brass component of the type described which customarily comes into contact with water is first treated in a hot caustic wash. As used herein, the caustic wash is an aqueous solution of an alkali metal hydroxide and preferably sodium or potassium hydroxide having a pH above 10, and preferably above 12. In general, the concentration of alkali metal hydroxide in the aqueous solution is an amount sufficient to remove substantially all of the hydroxide-leachable lead from the brass part. In general, use can be made of caustic solutions containing from about 10 to about 50 percent alkali metal hydroxide, although higher and lower amounts of caustic may be used, depending somewhat on the treatment time desired. In general, the more concentrated the alkali metal hydroxide in solution, the shorter is the treatment time necessary to remove at least 50 percent of the leachable lead.

Another parameter affecting the treatment time for the caustic solution is the temperature. In general, higher temperatures favor shorter treatment times while lower temperatures generally necessitate longer treatment times. Best results are obtained when the temperature of the caustic solution is at least 80° F, and preferably ranges from about 100° F to about 200° F. It is also frequently desirable to employ ultrasonic agitation of the caustic bath or the parts therein to insure maximum contact between the caustic solution and the brass. Good results are typically obtained when the entire caustic bath is subjected to



ultrasonic agitation. For example, it has been found that, using ultrasonic agitation, nearly all of the hydroxide-leachable lead can be removed from the brass components in the first several minutes of treatment. Good results are obtained, depending somewhat on the temperature, the concentration and the degree of agitation, when the treatment time ranges from about one minute to about 60 minutes.

After the component has been treated with the hot caustic wash, it is then rinsed with water, and preferably deionized water, to remove any dirt adhering to the surfaces of the components as well as to remove excess alkali metal hydroxide and any lead present on the surface of the parts. The rinsing time can be varied within wide limits, but generally a rinse extending from about 0.5 to about 30 minutes is sufficient.

Thereafter, the brass component is treated with carboxylic acid to remove substantially all of the leachable lead remaining on the component. Use is preferably made of a water soluble carboxylic acid containing from 1 to 8 carbon atoms and from 1 to 4 carboxyl groups. Representative of such acids are acetic acid, propionic acid, butyric acid, iso-butyric acid, citric acid, and the like. The concentration of the acid in aqueous solution can be varied within relatively wide ranges, depending again on the temperature of the acid treatment and the duration of the acid treatment. Good results are usually obtained when the concentration of the carboxylic acid ranges from about 0.01 to about 1.0 M. Once again, at least 50 percent of the acid-leachable lead is removed from the brass component during the first several minutes of treatment. In general, however it is preferred to employ acid treatment times ranging from about one minute to about 45 minutes. As will be appreciated by those skilled in the art, the use of additional treatment times is useful in the cleaning of the parts to remove

deposits remaining from casting of the parts using well-known core casting techniques. Best results are typically obtained when the acid employed is acetic acid, although citric acid likewise provides highly beneficial results.

As with the caustic bath, it is also frequently desirable to employ ultrasonic agitation of the carboxylic acid bath or the parts therein to insure maximum contact between the carboxylic acid solution and the brass. Good results are typically obtained when the entire carboxylic acid bath is subjected to ultrasonic agitation.

It has been found that the combination of caustic followed by acid treatment removes substantially all of the leachable lead from the part. It has been found that the removal rate of lead can be up to two times greater in the caustic treatment step compared to that achieved for subsequent acid washing steps.

As will be appreciated by those skilled in the art, both the caustic and acid treatment steps can either be carried out in a single step in which the brass component is contacted with either the caustic solution or acid solution. As an alternative, however, it is possible, and sometimes desirable, to use a series of caustic and/or acid treatment steps. It has been found that the use of the series of treatment steps has the advantage of providing increased rates of lead removal, particularly where the treatment solutions are more dilute. Without limiting the invention as to theory, it is believed that the concentration driving force between the lead in the part and lead contained in the solution is greater when use is made of a series of caustic and/or acid treatment steps to thermodynamically drive the reactions.

One of the advantages in the practice of the invention is that the sequence of caustic and acid treatment of the brass components exhibits no wholesale attack on the brass. On the contrary, the treatment process is limited primarily to lead removal, although there can be observed some removal of zinc during the caustic wash step. Once again, without limiting the invention as to theory, the removal of zinc can be attributed to the solubility of zinc complexes at high pH and possible surface enrichment of zinc during casting of the parts.

In the optional final step of the process, the components are treated with a phosphorus-containing acid, acid salt or salt derived from alkali metal, and preferably phosphoric acid. Also suitable are alkali metal salts of phosphoric acid and alkali metal acid salts of phosphoric acid (e.g., trisodium phosphate, monosodium phosphate and disodium phosphate). Without limiting the invention as to theory, it is believed that the treatment with the carboxylic acid chemically etches the brass component, leaving a weak electrical charge. When that weakly charged brass component is rinsed with phosphoric acid, for example, most of the remaining residual trace amounts of lead, if any, are removed, and the brass component is passivated, with residual lead, if any, forming a relatively insoluble lead-phosphate. It has been found that insoluble lead phosphate is relatively impervious to the action of water. Furthermore, the phosphate passivates the metal against corrosion, effectively minimizing any further leaching of metals from the brass component into water coming in contact with the brass component.

That, in turn, assures that any water coming in contact with the treated brass component contains very low levels of lead, generally below 11 parts per billion and typically below 5 parts per billion of lead in water.

As with the caustic and carboxylic acid bath, it is also frequently desirable to employ ultrasonic agitation of the phosphorus-containing acid bath or the parts therein to insure maximum contact between the phosphorus-containing acid solution and the brass. Good results are typically obtained when the entire phosphorus-containing acid bath is subjected to ultrasonic agitation.

In accordance with another alternative embodiment of the invention, it has been found advantageous, and particularly where the plumbing fixtures to be treated are formed from red brass, to employ a chemical milling pretreatment step by which surface metal is removed from the interior of such plumbing fixtures preparing the brass component for more effective removal of the leachable lead. As indicated, it is frequently preferred to employ a strong acid to remove surface metal from the interior of plumbing parts. Various acids can be used for that purpose, although it is preferred that the acid not be of such a strength as to cause excessive metal removal. As will be appreciated by those skilled in the art, the metal removal is determined not only by the acid employed, but also by its concentration, the time of immersion and the temperature. In general, use can be made of mineral acids such as hydrochloric acid, sulfuric acid, or nitric acid, either alone, or in combination with organic acids and preferably carboxylic acids. It has also been found that performance of such acids can, in appropriate cases, be enhanced through the use of oxidizing agents, and most notably peroxides (e.g.,  $H_2O_2$ ). It has been found that the use of such a chemical milling pretreatment step is particularly advantageous where, as a result of the casting operations, the interior of the plumbing fixtures undergoing treatment have a relatively high degree of surface roughness and residue.

In the preferred practice of the invention, it is also frequently desirable to rotate the various parts undergoing treatment during the treating operation. For example, such rotation can be effected during the time that the part is undergoing treatment during either the caustic or acidic treatment steps to remove air pockets which may be formed within the interior of the parts undergoing treatment. Thus the rotation of the parts during treatment ensures a more uniform treatment of the brass parts.

Having described the basic concepts of the invention, reference is now made to the following examples which are provided by way of illustration, and not by way of limitation, of the practice of the present invention.

#### General Procedure For Examples

Brass fixture components were treated by submerging in a sequence of chemical baths designed to leach lead from the components. Fixtures were held on racks that allowed free flow of solution into each fixture. The baths were prepared in tanks with ultrasonic generators and electric heater coils as described below.

The first bath contained 10% sodium hydroxide and deionized water. Two ultrasonic generators and one electric heater coil were installed. The temperature of the caustic solution was maintained at 150 deg. F. Fixtures were submerged for half of the specified duration, lifted from the tank, rotated 180 degrees along the vertical axis and submerged for the remainder of the duration.

The second bath was a water rinse at ambient temperature with no ultrasonics, however air agitation was used. Fixtures were submerged for a period of approximately 1 minute.

The third bath contained a 0.1M acetic acid pre-soak solution at ambient temperature. Parts were submerged for approximately 1 minute. No ultrasonics were used, however air agitation was used.

The fourth bath contained 0.1M acetic acid solution with four ultrasonic generators and two electric heater coils. Bath temperature was maintained at 120 deg. F. Fixtures were submerged in the bath for the specified duration then lifted out of the tank and rotated 180 degrees about the vertical axis. Fixtures were again submerged for the remainder of the specified duration.

The final three tanks were deionized water counter flowing rinses with air agitation used in the second tank and ultrasonics in the final tank with two ultrasonic generators and an electric heater coil. The final tank bath temperature was maintained at 140 deg. F.

Example #1

Three yellow brass castings each with a cold mix volume of .085 Liters were treated with the above procedure. Castings were submerged for five minutes in a caustic bath, five minutes in an acetic acid bath and five minutes in the final rinse of deionized water and phosphoric acid. The castings were then tested with procedures required by NSF Standard 61, Section 9. The Q statistic was then determined by formulas contained in NSF Standard 61, Section 9.

Day	Lead Detected [ug]			LN ug		
	1	2	3	1	2	3
3	2.21	2.30	2.64	0.79	0.83	0.97
4	1.62	1.62	1.79	0.48	0.48	0.58
5	1.28	1.19	1.45	0.25	0.17	0.37
10	0.85	0.84	1.02	-0.16	-0.17	0.02
11	0.68	0.72	0.85	-0.39	-0.33	-0.16
12	0.65	0.70	0.65	-0.43	-0.36	-0.43
17	0.41	0.54	0.59	-0.89	-0.62	-0.53
18	0.26	0.27	0.29	-1.35	-1.31	-1.24
19	0.43	0.37	0.43	-0.84	-0.99	-0.84
Average				-0.28	-0.25	-0.14
Mean				-0.23		
Std Dev				0.08		
Q Test Statistic				0.97		

Example #2

Three red brass castings each with a cold mix volume of .116 L Liters were treated with the same procedure as above. Castings were submerged for sixty minutes in a caustic bath, thirty minutes in an acetic acid bath and five minutes in the final rinse of deionized water and phosphoric acid. The castings were then tested with procedures required by NSF Standard 61, Section 9. The Q statistic was then determined by formulas contained in NSF Standard 61, Section 9.

Day	Lead Detected [ug]			LN ug		
	1	2	3	1	2	3
3	12.76	13.92	13.92	2.55	2.63	2.63
4	15.08	12.76	13.92	2.71	2.55	2.63
5	11.60	15.08	16.24	2.45	2.71	2.79
10	8.93	15.08	11.60	2.19	2.71	2.45
11	5.92	6.50	7.19	1.78	1.87	1.97
12	5.57	6.03	6.15	1.72	1.80	1.82
17	7.54	7.42	8.35	2.02	2.00	2.12
18	19.72	7.08	5.92	2.98	1.96	1.78
19	7.77	5.68	6.73	2.05	1.74	1.91
Average				2.27	2.22	2.23
Mean				2.24		
Std Dev				0.03		
Q Test Statistic				10.10		



Example #3

Three red brass castings each with a cold mix volume of .116 Liters were treated with the same procedure as above. Castings were submerged for sixty minutes in a caustic bath, thirty minutes in an acetic acid bath and five minutes in the final rinse of deionized water. The castings were then tested with procedures required by NSF Standard 61, Section 9. The Q statistic was then determined by formulas contained in NSF Standard 61, Section 9.

Day	Lead Detected [ug]			LN ug		
	1	2	3	1	2	3
3	6.15	6.73	7.42	1.82	1.91	2.00
4	4.64	6.73	4.99	1.53	1.91	1.61
5	4.18	6.15	4.99	1.43	1.82	1.61
10	3.02	3.71	15.08	1.11	1.31	2.71
11	2.44	3.25	3.02	0.89	1.18	1.11
12	2.20	2.90	3.25	0.79	1.06	1.18
17	2.32	3.71	3.02	0.84	1.31	1.11
18	5.10	2.09	4.87	1.63	0.74	1.58
19	1.86	4.06	2.44	0.62	1.40	0.89
Average				1.18	1.40	1.53
Mean				1.37		
Std Dev				0.18		
Q Test Statistic				6.26		

It will be understood that various changes can be made in the details of procedure, formulation and use without departing from the spirit of the invention, especially as defined in the following claims.

What Is Claimed:

1. A process for the treatment of brass components to reduce leaching lead therefrom when the component is exposed to water, comprising:
  - a) contacting the brass component with an aqueous caustic solution to remove some of the leachable lead from the brass component,
  - b) rinsing the brass components to remove excess caustic solution, and
  - c) contacting the brass component with a water soluble carboxylic acid to remove most of the remaining leachable lead.
2. A process as defined in claim 1 wherein the brass components are treated for a time sufficient to provide a brass component which, when contacted with water, provides a water stream containing less than 11 parts per billion of lead.
3. A process as defined in claim 1 wherein the brass components are treated for a time sufficient to provide a brass component which, when contacted with water, provides a water stream containing less than 5 parts per billion of lead.
4. A process as defined in claim 1 wherein the caustic is selected from the group consisting of sodium hydroxide and potassium hydroxide.

5. A process as defined in claim 1 wherein the caustic solution has a pH above 10.

6. A process as defined in claim 1 wherein the component is contacted with the aqueous caustic solution for a time sufficient to remove at least 50% of the leachable lead.

7. A process as defined in claim 1 wherein the brass component is contacted with the aqueous caustic solution maintained at a temperature within the range of about 100°F to about 200°F.

8. A process as defined in claim 1 wherein the brass component is contacted with the aqueous caustic solution which is ultrasonically agitated to maintain contact between the caustic solution and the brass component.

9. A process as defined in claim 1 wherein the brass component is contacted with the aqueous caustic solution for a time ranging from about 1 minute to about 60 minutes.

10. A process as defined in claim 1 wherein the brass component is rinsed for a time sufficient to remove any dirt adhering to the component and to remove substantially all of the excess caustic solution.

11. A process as defined in claim 1 wherein the brass component is rinsed in water.

12. A process as defined in claim 1 wherein the carboxylic acid contains from 1 to 8 carbon atoms and from 1 to 4 carboxyl groups.

13. A process as defined in claim 1 wherein the carboxylic acid is selected from the group consisting of acetic acid and citric acid.

14. A process as defined in claim 1 wherein the concentration of the carboxylic acid ranges from about 0.01 to about 1.0 molar.

15. A process as defined in claim 1 wherein the brass component is pretreated with a strong acid to remove surface matter and reduce surface roughness of the interior of the component.

16. A process as defined in claim 1 wherein the strong acid is a mineral acid used in combination with a carboxylic acid and a peroxide oxidizing agent.

17. A process as defined in claim 1 which includes the step of rinsing the brass component with a phosphorous-containing acid, acid salt or salt derived from alkali metal to remove any residual trace amounts of leachable lead, if any, from the brass component and passivate the metal to substantially eliminate any further leaching of lead when the brass component is exposed to water.

18. A process for the treatment of brass components to reduce leaching lead therefrom when the component is exposed to water comprising:

- a) contacting the brass component with an aqueous caustic solution to remove some of the lead from the brass component,
- b) rinsing the brass components with water, and

- c) contacting the brass component with a water soluble carboxylic acid to remove most of the remaining leachable lead.

with at least one of the aqueous caustic treatment and carboxylic acid treatment being effected in the presence of ultrasonic agitation.

19. A process as defined in claim 18 which includes the step of rotating the component during contact with the aqueous caustic solution and/or during contact with the carboxylic acid to remove air pockets and promote uniform treatment of the brass component.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/00008

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C23F1/00 E03C1/04

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C23F E03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PAIGE J L ET AL: "LEACHABILITY OF LEAD FROM SELECTED COPPER-BASE ALLOYS" CORROSION, vol. 48, no. 12, 1 December 1992, HOUSTON US, pages 1040-1046, XP000560262 see page 1045	1, 18
A	EP 0 683 245 A (IMI YORKSHIRE FITTINGS) 22 November 1995 see claims 1-3, 11; table 2	17
A	US 5 454 876 A (DOWNEY JEROME P) 3 October 1995	
A	DE 36 19 881 A (WMF WUERTTEMBERG METALLWAREN) 17 December 1987	

-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 May 1998

Date of mailing of the international search report

27/05/1998

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.

Authorized officer

Torfs. F

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int'l Application No

PCT/US 98/00008

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0683245 A	22-11-1995	AU 2003795 A	23-11-1995
		CA 2149499 A	18-11-1995
		CN 1114367 A	03-01-1996
		GB 2289478 A,B	22-11-1995
		HU 75844 A	28-05-1997
		PL 308618 A	27-11-1995
		ZA 9503740 A	11-01-1996
US 5454876 A	03-10-1995	AT 164650 T	15-04-1998
		AU 684200 B	04-12-1997
		AU 2830395 A	15-02-1996
		CN 1122844 A	22-05-1996
		DE 69501928 D	07-05-1998
		EP 0695833 A	07-02-1996
		JP 8061586 A	08-03-1996
		SG 30427 A	01-06-1996
		ZA 9505747 A	20-02-1996
DE 3619881 A	17-12-1987	NONE	
DE 3422327 A	19-12-1985	NONE	
WO 9706313 A	20-02-1997	AU 3085795 A	05-03-1997